



HK Stain

Solvent-based premium wood preservative stain with excellent moisture protection for exterior wood



Colour	Availability	Quantity per pallet				
		672	200	96	30	22
	Size / Quantity	3 x 0,75 l	2 x 2,5 l	1 x 5 l	10 l	20 l
	Type of container	Tin bucket	Tin bucket	Tin bucket	Tin bucket	Tin bucket
	Container code	01	03	05	10	20
Art. no.						
pine/larch (RC-260)	2250	■	■	■	■	■
teak (RC-545)	2251	■	■	■	■	■
ebony (RC-790)	2252	■	■	■	■	■
chestnut (RC-555)	2253	■	■	■	■	■
fir green (RC-960)	2254	■	■	■	■	■
mahogany (RC-565)	2255	■	■	■	■	■
palisander (RC-720)	2256	■	■	■	■	■
nutwood (RC-660)	2260	■	■	■	■	■
clear	2261	■	■	■	■	■
pine (RC-270)	2262	■	■	■	■	■
rustic oak (RC-360)	2263	■	■	■	■	■
light oak (RC-365)	2264	■	■	■	■	■
hemlock (RC-120)	2266	■	■	■	■	■
white (RC-990)	2268	■	■	■	■	■
salt green (RC-965)	2292	■	■	■	■	■
special colours*	2267		■	■	■	■

*Minimum order quantity 2.5 l

Application rate

Approx. 100 ml/m² per coat, at least 2 coats required

Planned or very thick woods are less absorbent and may require a third coat



Range of use



- For use on exterior wood
- Wood without ground contact
- Wood building elements with no dimensional stability: e.g. fences, framework, carports, planking
- Wood building elements with limited dimensional stability, e.g. folding shutters, matchboarding, summerhouses
- Dimensionally stable wood building elements (when used as a primer only): e.g. windows and doors
- Primer, intermediate and finishing coats
- Not suitable for coating floors (terraces, wooden decking, etc.)

Property profile



- 3 in 1: impregnation, priming and stain
- Protects wood from moisture and UV radiation
- Impregnation effect: saturates wood to protect against moisture
- Diffusion-open protective film: moisture can escape
- Water-repellent: wet surfaces dry quickly
- Protection against weathering (constructive protection and the protection provided by the product) reduces the risk of blue stain and rot



- Increased solids content provides physical protection against nesting wasps
- Coating is protected against mould and algae
- Subsequent treatment without sanding
- Low-build stain
- Brilliant colours
- Does not flake
- All colours are mixable with one another

Characteristic data of the product

Binder	Alkyd resin
Density (20 °C)	Approx. 0.87 g/cm ³
Viscosity (20 °C)	Approx. 80 s ISO 2431/3 mm
Pigmentation	Light-fast, highly transparent pigments
Flash point °C	> 60 °C
Odour	Solvent-like, odourless once dry
Degree of gloss	Silk matt

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

Additional information

- [Colour card](#)
- [Grey Protect colour card](#)

Possible system products

- [Long Life Stain UV \(2234\)](#)
- [End Grain Sealer \(1900\)](#)

Preparation

- **Substrate requirements**
Dimensionally stable wood building elements: wood moisture content 11-15%
Wood building elements with limited or no dimensional stability: wood moisture content max. 18%
- **Substrate preparation**
Completely remove old coatings (e.g. paints or medium-build stains), bark, bast and dirt.
Remove loose and torn knots as well as resin that bleeds and clean with a suitable product (e.g. thinner & brush cleaner).
Smooth, planed wood surfaces should be sanded and dusted before the coating is applied to ensure better absorption.
Observe BFS Code of Practice No. 18 "Coatings on Wood and Wooden Working Materials in Outdoor Areas".

Directions



- **Conditions for use**
Temperature of the material, air and substrate: from min. +5 °C to max. +30 °C.

Stir well.
Private users: Application by brush.
Professional operations: Application by brush, dipping, flow coating; spraying only in closed facilities.
Apply in the direction of the grain.
Apply a second coat once the first has dried.
On oak an additional, clear base coat is recommended.
Seal opened containers well and use contents as soon as possible.

Tips on use



- Check colour, adhesion and compatibility with the substrate by setting up a trial area.
If the surface is overcoated with other products it is recommended to test the adhesion to the substrate.
Clear, white and hemlock are suitable for use only on not directly weathered surfaces in outdoor areas, such as roof eaves, or as base coat.
Rainfall may cause water soluble substances to bleed from wood that is rich in such substances, e.g. oak, red cedar, afzelia, redwood, etc. This may lead to the discolouration of light-coloured masonry or render.
Pre-testing is recommended also on other woods.
Cut end-grain surfaces at the bottom to create a water-drip edge.
Apply two subsequent coats of end-grain wood preservative to end-grain wood and cut surfaces in order to protect them against moisture.
Each layer of medium-build stain results in a more intense colour and a glossier finish.
- **Drying**
Approx. 12 hours at 20 °C and 65% relative humidity.
Low temperatures, poor ventilation and high humidity delay drying.
Even once the coating is sufficiently dry for handling, less volatile solvents may cause surface to feel clammy to the touch over several days!
This property does not constitute a flaw!
The evaporation of these solvents can be accelerated by the ensuring the highest possible air exchange.
- **Thinning**



Ready to use

Notes On planed larch and softwoods with a high resin content, the coating may have reduced adhesion and resistance to weathering. This is especially the case on horizontal year rings, knots and areas of winter growth that are high in resin. Maintenance and renovation must be carried out more frequently on these surfaces. The only remedy for this is pre-weathering or very coarse sanding (P80). If these wood types are rough-sawn, considerably longer maintenance and renovation intervals are to be expected.

Tools / Cleaning


Brush with natural bristles, flat brush



Clean tools immediately after use with thinner and brush cleaner.
Ensure that any residue from cleaning is disposed of correctly.

Storage / Shelf life

At least 36 months in unopened, original containers stored cool, dry and protected from frost.



Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.

Biocidal Products Regulation

Contains as "treated goods" a biocidal product (film preservative) with the biocidal active agent 3-iodo-2-propynyl butylcarbamate to protect the film from contamination by microbial organisms (algae, mould etc.). Always follow the directions carefully!

VOC content as per the "Decopaint" Directive (2004/42/EC)

EU limit value for the product (Cat. A/e): max. 400 g/l (2010).
This product contains < 400 g/l VOC.

VOC	
Kat.	A/e
2010:	400g/l
max.:	400g/l

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.