



## Arte Mundit

Solvent-free, skin-forming peel-off paste for water-free removal of dust, soot and other impurities

Type/Name	Availability						
	Quantity per pallet			22			
	<b>Size / Quantity</b>	<b>0,2 kg</b>		<b>15 kg</b>	<b>15 kg</b>	<b>15 kg</b>	<b>15 kg</b>
	Type of container	Sample tin	Sample tin		Tin bucket + additive	Tin bucket + additive	Tin bucket + additive
	Container code	83	81	16	16	18	19
	<b>Art. no.</b>						
Type 1: pure natural latex dispersion	222020	■		■			
Type 2: natural latex dispersion + additive	222023		■		■		
Type 3: natural latex dispersion + additive	222025		■			■	
Type 5: natural latex dispersion + additive	222028		■				■

### Application rate

Approx. 1.0 kg/m<sup>2</sup> on flat surfaces  
Approx. 1.0 – 3.0 kg/m<sup>2</sup> on highly textured surfaces  
Apply to a large enough trial area to determine the precise amount required.



### Range of use



- Delicate and valuable interiors
- Surface contamination on stucco, natural stone, marble, concrete, brick, render, gypsum sculptures, polished wood and synthetic building materials
- Type 1  
Physical cleaning for lightly adhering dirt
- Type 2  
Special cleaner for marble
- Type 3  
Physical and chemical cleaning for general impurities
- Type 5  
Especially for cleaning fire residue
- For use by professionals

### Property profile

- Self-activating cleaning with deep action
- Forms a film and binds dirt
- Dust-free cleaning without additional water
- Solvent-free
- Contains a complexing additive, can be configured to suit the substrate and type of contamination

### Characteristic data of the product

Density (20 °C)	Component A: 0.94 g/ml Component B: 1.05 - 1.20 g/ml depending on type
pH value (20 °C)	Component A: approx. 10.0 depending on type Component B: 10.0 - 11.0 depending on type

The values stated represent typical characteristic data of the product and are not to be understood as binding product specifications.

### Certificates

➤ [Zusätzliche technische Informationen](#)

### Preparation

- Substrate requirements  
The substrate being cleaned must be dry and free from dust and loose debris.



- **Substrate preparation**  
Use a suitable tool to coarsely clean off the substrate.  
Set up a trial area to determine the cleaning effect.  
Take appropriate measures to protect adjacent building elements and materials that should not come into contact with the product.

#### Directions



For professional users only!

- **Conditions for use**  
Temperature of the material, air and substrate: from min. +5 °C to max. +30 °C.

Stir the material thoroughly using a suitable tool.  
If necessary, stir in component B thoroughly.  
Apply with suitable tools to the full substrate area.  
Apply material over the entire surface manually or by airless spraying.  
Fill undercut areas and contours thoroughly with the material.  
After 24 hours and once completely dry, remove the film by pulling it off, keeping the tensile force as constant as possible.  
Cleaned surfaces can be further cleaned with a damp sponge or medium-hard brush (nylon bristles).  
Use as little water as possible.

#### Tips on use

Please contact Remmers Technical Service (phone +49 5432 83900) before applying with machine processing.

#### Notes

The specified mixing ratios must be carefully observed.  
The relevant test certificates must be observed when planning and carrying out work.  
Always set up a trial area/trial areas first.  
Deviations from applicable regulations must be agreed separately.

#### Tools / Cleaning




Brush, lamb's wool roller, spreader and smoothing trowel  
Airless spraying equipment  
Stainless steel or plastic tools are recommended.  
Clean tools immediately after use with water and detergent.

Remmers tools

- [Flächenstreicher \(4540\)](#)
- [Farbrolle FC \(4913\)](#)
- [Rollerbügel \(4449\)](#)
- [Epoxy Roller \(5045\)](#)
- [Nylon Roller Standard \(5066\)](#)
- [Heizkörperpinsel \(4541\)](#)

#### Storage / Shelf life



If stored unopened in the original container and kept cool, dry and protected from frost, min. 12 months (component A)/min. 24 months (component B).

#### Safety data / Regulations

For further information on the safety aspects of transporting, storing and handling the product and on disposal and environmental matters, please see the current Safety Data Sheet.

#### Personal protective equipment

Respiratory protection with a particle filter P2 must be worn during spraying, together with protective goggles. Wear suitable protective gloves and clothing.

#### Disposal

Larger quantities of leftover product should be disposed of in the original containers in accordance with the applicable regulations. Completely empty, clean containers should be recycled. Do not dispose of together with household waste. Do not allow to enter the sewage system. Do not empty into drains.  
Any material that is contaminated after application must be disposed of in accordance with the applicable regulations.

Please note that the data and information given above have been calculated as guidelines in the laboratory and from real-life experience and are therefore not binding as a basic principle.

This information is therefore of a general nature only and describes our products and how they are used and worked with. In this respect, it must be borne in mind that the varied and diverse nature of the

prevailing working conditions, materials used and construction sites encountered means that not every individual case can be covered. In this respect, we therefore recommend either conducting tests or liaising with us in the event of any doubt. Unless we have provided express written assurance of the products' specific suitability or characteristics in respect of a contractually stipulated intended use, any technical application-related advice or instruction will never

be binding, even though it is provided to the best of our knowledge. In all other respects, our general terms and conditions of sale and delivery shall apply.

When a new version of this Technical Data Sheet is published, it shall replace the previous version.